MANUFACTURER

SOLAR INNOVA GREEN TECHNOLOGY, S.L.
N.I.F.: ESB-54.627.278
Paseo de los Molinos, 12
03660 - NOVELDA (Alicante) SPAIN
T/F: +34965075767
E: info@solarinnova.net
W: www.solarinnova.net

PHOTOVOLTAIC MODULES

Series BIPV-FENCES **Reference** SI-ESF-M-BIPV-FC-M158-50 **Type** MONOCRYSTALLINE

INTRODUCTION





MATERIALS Solar Innova uses the latest materials to manufacture photovoltaic modules.

USE Our modules are ideal for any application that uses the photoelectric effect as a clean energy source because of its minimal chemical pollution and no noise pollution.

FRONT The front of the module contains a tempered solar glass with:
- High transmissivity.
- Low reflectivity.
- Low iron content.

PV CELLS These PV modules use high-efficiency monocrystalline silicon cells (the cells are made of a single crystal of high purity silicon) to transform the energy of sunlight into electric energy.

Each cell is electrically rated to optimize the behavior of the module.

Its performance is excellent over the entire range of light spectrum, with particularly high yields in low light situations or cloudiness to direct sunlight (diffuse radiation).



ENCAPSULANT The cell circuit is laminated using as encapsulant:
- PVB (Polivinil Butiral).

BACK The rear of the module contains a tempered glass which provides complete protection and seals against environmental agents and electrical insulation.

JUNCTION BOX The junction boxes with IP67, are made from high temperature resistant plastics and containing terminals, connection terminals and protection diodes (by-pass).

These modules are supplied with symmetric lengths of cable, with a diameter of copper section of 4 mm and an extremely low contact resistance, all designed to achieve the minimum voltage drop losses.

PERFORMANCE Our modules comply with all safety requirements not only flexibility but also double insulation and high resistance to UV rays, all are suitable for use in outdoor applications. The design of these modules makes their integration in both industrial and residential buildings (one of the most emerging sectors in the photovoltaic market), and other infrastructure, simple and aesthetic.

QUALITY CONTROL We have quality control divided into three elements:
- Regular inspections allow us to guarantee the quality of the raw material.
- Quality control in the process of our manufacturing procedures.
- Quality control of finished products, we conduct through inspections and tests of reliability and performance.

WARRANTIES Our manufacturing plants have been prepared in accordance with:
- ISO 9001, in terms of Quality Systems and Business.
- ISO 14001, in terms of Environmental Management Systems.
- ISO 45001, in terms of Management Systems Health and Safety.

CERTIFICATES Our PV modules are certified by internationally recognized laboratories and are proof of our strict adherence to international safety standards, long term performance and overall quality of products.



MANUFACTURER

SOLAR INNOVA GREEN TECHNOLOGY, S.L.
N.I.F.: ESB-54.627.278
Paseo de los Molinos, 12
03660 - NOVELDA (Alicante) SPAIN
T/F: +34965075767
E: info@solarinnova.net
W: www.solarinnova.net

PHOTOVOLTAIC MODULES

Series	BIPV-FENCES	Reference	SI-ESF-M-BIPV-FC-M158-50	Type	MONOCRYSTALLINE

PV CELLS

Type	Monofacial		sc-Si

MECHANICAL CHARACTERISTICS			TEMPERATURE COEFFICIENTS		
Size	mm	158,75 x 158,75 ±0,25	Tk Voltage	%/K	-0,36
Thickness	µm	180 ±20	Tk Current	%/K	0,06
Front	[-]	Si3N4 anti-reflection coating	Tk Power	%/K	-0,36
Back	[+]	Aluminum back surface field (Al-BSF)			

PV MODULES

ELECTRICAL CHARACTERISTICS

STC CONDITIONS

Maximum power	[Pmpp]	Wp	275	±3% (*)
Power selection	[Pmpp]	%	±3	
Voltage at maximum power	[Vmpp]	V	29,01	IEC 60904-1
Current at maximum power	[Impp]	A	9,48	IEC 60904-3
Open circuit voltage	[Voc]	V	34,17	±3% (*)
Short circuit current	[Isc]	A	10,04	±4% (*)
Maximum system voltaje	[Vsyst]	V	1500 / 1000	IEC / UL
Maximum series fuse rating	[Icf]	A	15	
Efficiency	[ηm]	%	13,75	
Form Factor	[FF]	%	80,17	

STC (Standard Test Conditions): Irradiance: 1000 W/m2 + Cell Temperature: 25º C + Air Mass: 1.5

* (Considering LID, the power range of the certification authority)

NMOT CONDITIONS

Maximum power	[Pmpp]	Wp	203	IEC 61215
Voltage at maximum power	[Vmpp]	V	26,41	
Current at maximum power	[Impp]	A	7,70	
Open circuit voltage	[Voc]	V	31,23	
Short circuit current	[Isc]	A	8,14	

NMOT (Nominal Module Operating Temperature): Irradiance: 800 W/m2 + Ambient Temperature: 20º C + Air Mass: 1.5 + Wind Speed: 1 m/s

MECHANICAL CHARACTERISTICS

PANEL	WIDTH (X)		HIGH (Y)		DIAGONAL		AREA	POWER/AREA
Size - Glass-1	2000	x	1000	mm			2,00 m2	137 Wp/m2
Size - Glass-2	2000	x	1000	mm			2,00 m2	
CELLS								
Size	158,75	x	158,75	mm	223 mm		0,03 m2	
Distance - Top			73	mm				
Distance - between Cells	15	x	15	mm				
Distance - Left	139	mm						
Distance - Right	139	mm						
Distance - Bottom			73	mm				
Quantity	10	x	5	=	50 units		1,26 m2	

COMPONENTS

MATERIAL	QUANTITY		THICKNESS (Z)		DESCRIPTION	DENSITY	TOTAL WEIGHT	THERMAL RESISTANCE
Glass-1	1	units	8	mm	FTG-UClear	20,25 kg/m2	40,50 kg	0,1776 m2K/W
Sheet Encapsulant	1	units	0,76	mm	PVB	0,81 kg/m2	1,62 kg	0,0032 m2K/W
Busbars	5	units	1	mm	CuSn6	0,10 kg/m2	0,13 kg	
PV Cells	50	units	0,21	mm	sc-Si	0,20 kg/m2	0,25 kg	
Sheet Encapsulant	1	units	0,76	mm	PVB	0,81 kg/m2	1,62 kg	0,0032 m2K/W
Glass-2	1	units	8	mm	FTG	20,25 kg/m2	40,50 kg	0,1776 m2K/W
Junction Box	1	units	10	mm	PVC-IP68	0,10 kg/m2	0,10 kg	
Diodes (By-pass)	2	units				0,01 kg/m2	0,02 kg	
Cables (+/-)	2	units	4	mm2	900 mm	0,10 kg/m2	0,20 kg	
Connectors	2	units	MC3	type	PVC-IP67	0,05 kg/m2	0,10 kg	
TOTAL			**17,73**	**mm**		**42,67 kg/m2**	**85,02 kg**	**0,36 m2K/W**

THERMAL CHARACTERISTICS

TEMPERATURE COEFFICIENTS		MONOCRYSTALLINE		
Temperature coefficient of short circuit current	α	[Isc]	0,0700	%/º C
Temperature coefficient of open circuit voltage	β	[Voc]	-0,3600	%/º C
Temperature coefficient of maximum power	γ	[Pmpp]	-0,3800	%/º C
Temperature coefficient of current at maximum power		[Impp]	0,1000	%/º C
Temperature coefficient of voltage at maximum power		[Vmpp]	-0,3800	%/º C
Nominal Module Operating Temperature		[NMOT]	+ 47 ± 2	º C

THERMAL TRANSMITTANCE (U)				SOLAR HEAT GAIN COEFFICIENT (G)		
Ug-value	2,77 W/m2 K		EN 673	G-value	0,36 %	EN 410
UV TRANSMITTANCE				**ACOUSTIC INSULATION (R)**		
UV-Value	1,50 %	300-380 nm	EN 410	R-value	32(-1:-3)	EN 12758
VISIBLE LIGHT TRANSMISSION (LT)						
LT-value	37,00 %	380-780 nm	EN 410	Opacity	63,00 %	CIE D65 ISO 9050
EXTERIOR REFLECTION (LRe)				**INTERIOR REFLECTION (LRi)**		
RLi-value	8,00 %		EN 410	RLe-value	15,00 %	EN 410

TOLERANCES

Working temperature	- 40 / + 85 ºC			Glass dimension	< ± 2,5 mm	EN 12543-5
Dielectric isolation voltage	3000 V			Glass symmetrytolerance	< ± 3 mm	EN 12543-5
Relative humidity	0 / 100 %			Cell single string distolerance	< ± 1 mm	EN 12543-6
Wind resistance	2400 Pa	245 kg/m2				IEC 61215
Snow resistance	28800 Pa	2937 kg/m2		Maximum hail resistance	Ø 35	97 m/s IEC 61215
Conductivity at ground	≤ 0.1 Ω			Resistance	≥ 100 Ω	

CLASSIFICATIONS

Application class	A Class		IEC 61730	Pollution	1 Degree	IEC 61730
Electrical protection class	II Class	IEC 61140	IEC 61730	Material	I Group	IEC 61730
Fire safety class	A Class	ANSI/UL 790	IEC 61730	Safety	1.5 Factors	IEC 61730

LAMINATED GLASS (EN 14449)

Impact resistance	1B1 Class		EN 12600	High temperature	OK	EN 12543-4
Manual attack	P2A Class		EN 356	Humidity	OK	EN 12543-4

MANUFACTURER

SOLAR INNOVA GREEN TECHNOLOGY, S.L.
N.I.F.: ESB-54.627.278
Paseo de los Molinos, 12
03660 - NOVELDA (Alicante) SPAIN
T/F: +34965075767
E: info@solarinnova.net
W: www.solarinnova.net

PHOTOVOLTAIC MODULES

Series	BIPV-FENCES	Reference	SI-ESF-M-BIPV-FC-M158-50	Type	MONOCRYSTALLINE

DRAWING

JUNCTION BOX

Position	Front	-	Rear	-	Edge	■	Axis (X)	■	Axis (Y)	-

PANEL

FRONT



REAR



SECTION



WIDTH (X) 2000 mm

THICKNESS (Z) 17,73 mm

PERFORMANCE

CELLS

TEMPERATURE

Temperature depending on Isc, Voc and Pmax



IRRADIANCE

Irradiance depending on Isc, Voc and Pmax
(cell temperature: 25º C)



PANELS

TEMPERATURE

Electrical performance
(cell temperature: 25º C)



I-V 1000 W/m2	P-I 1000 W/m2
I-V 800 W/m2	P-I 800 W/m2
I-V 600 W/m2	P-I 600 W/m2
I-V 400 W/m2	P-I 400 W/m2
I-V 200 W/m2	P-I 200 W/m2

IV-IRRADIANCE



I-V (-25ºC) I-V (0ºC) I-V (+25ºC) I-V (+50ºC) I-V (+75ºC)

SOLAR SIMULATOR

Class	AAA	IEC 60904-9	Power measurement uncertainty is	± 3 %

ELECTRICAL MEASURES

STC CONDITIONS			NMOT CONDITIONS		
Irradiance	1000 W/m2	IEC 60904-1	**Irradiance**	800 W/m2	IEC 61215
Cell temperature	25 ºC	IEC 60904-3	**Ambient temperature**	20 ºC	
Air Mass	1,5	ASTM G173	**Air Mass**	1,5	ASTM G173-03
		ASTM 1036	**Wind speed**	1 m/s	

MANUFACTURER

SOLAR INNOVA GREEN TECHNOLOGY, S.L.
N.I.F.: ESB-54.627.278
Paseo de los Molinos, 12
03660 - NOVELDA (Alicante) SPAIN
T/F: +34965075767
E: info@solarinnova.net
W: www.solarinnova.net

PHOTOVOLTAIC MODULES

Series	BIPV-FENCES	Reference	SI-ESF-M-BIPV-FC-M158-50	Type	MONOCRYSTALLINE

STANDARD GUARANTEES

LINEAR PERFORMANCE WARRANTY



Manufacturing defects	12 years.			
Performance	90 %	of rated power after	12	years of operation,
	80 %	of rated power after	25	years of operation.
Lifespan	> 30 years.			

ENVIRONMENTAL INFORMATION

				kWh	Coal	Petrol/Gas	Combined	
Solar Hours Peak	6 day							
Irradiation rate	1000 W/ m2			1	0,961	0,828	0,372	kg/CO2
Energy generated	1,65 kWh/ day	**Avoid**		**day**	1,59	1,37	0,61	kg/CO2
	49 kWh/ month	**CO2**		**month**	47,57	40,99	18,41	kg/CO2
	602 kWh/ year	**emissions**		**year**	578,76	498,66	224,03	kg/CO2

CERTIFICATES

ISO 9001	Quality Management Systems.
ISO 14001	Environmental Management Systems.
ISO 45001	Occupational Health and Safety Management Systems.
CE	Directive 2014/35/EU of the European Parliament and of the Council of 26 February 2014 on the harmonisation of the laws of the Member States relating to the making available on the market of electrical equipment designed for use within certain voltage limits.
IEC/EN 61215	Crystalline silicon terrestrial photovoltaic (PV) modules. Design qualification and type approval.
IEC/EN 61730-1	Photovoltaic (PV) module safety qualification - Part 1: Requirements for construction.
IEC/EN 61730-2	Photovoltaic (PV) module safety qualification - Part 2: Requirements for testing.
IEC 63092-1	Photovoltaics in buildings - Part 1: Requirements for building-integrated photovoltaic modules.
UL 1703	Standard for Flat-Plate Photovoltaic Modules and Panels.
EN 13501	Fire classification of construction products and building elements - Part 1: Classification using data from reaction to fire tests.
EN 14449	Glass in building - Laminated glass and laminated safety glass - Evaluation of conformity/Product standard.
EN 12543	Glass in building - Laminated glass and laminated safety glass.
EN 12600	Glass in building - Pendulum test - Impact test method and classification for flat glass.
EN 50583	Photovoltaics in buildings - Part 1: BIPV modules.

PACKING

CONTAINER 20'			CONTAINER 40'HQ		
PANELS X PALLET	**PALLETS**	**TOTAL**	**PANELS X PALLET**	**PALLETS**	**TOTAL**
-	-	-	26	22	572

IEC 62759-1	Photovoltaic (PV) modules - Transportation testing - Part 1: Transportation and shipping of module package units.

EXPORT INFORMATION

HS Code	85.41.43.00	**TARiC code**	85.41.43.00

REGISTER OF ELECTRICAL AND ELECTRONIC EQUIPMENT PRODUCERS

WEEE	7378	**Entity**	ECOASIMELEC

DESCRIPTION

Silicon cell photovoltaic solar module sc-Si, BIPV-Fences series, for architectural integration, from the manufacturer SOLAR INNOVA, maximum power (Wp) 274 W, voltage at maximum power (Vmp) 29,01 V, current at maximum power (Imp) 9,48 A, open-circuit voltage (Voc) 34,17 V, short-circuit current (Isc) 10,04 A, efficiency 13,75 %, composed of 50 cells, front layer tempered glass thick 8 mm, encapsulant layers of cells of PVB, back layer of tempered glass thick 8 mm, junction box (diodes, cables 4 mm2, 900 mm and connectors MC3), working temperature - 40 / + 85 ºC, dimensions 2000 x 1000 x 17,73 mm, maximum wind load 2400 Pa, maximum snow load 28800 Pa, weight 85,02 kg.

COMMENTS

NOTICE

The specifications and technical data may be subject to possible modifications without notice.
This data sheet are conform to the requirements of the Standard EN 50380.
Images for ilustration purposes only.